

Product data sheet, June 2010

# Vivak® Design

## Frosted solid copolyester sheets



### Advantages:

- exclusive appearance
- excellent thermoformability
- good impact strength
- high fire rating

**Vivak® Design** are frosted solid sheets made of thermoplastic copolyester. They offer high impact strength, a good fire rating and are fully recyclable.

### Applications:

**Vivak® Design** is ideally suited for use in partition walls, furniture, light elements, POS (displays, shelf partitions), trade show booths (walls, floors, pillars, etc.), shop-fitting systems, direction signs, advertising symbols and partitions.

**Vivak® Design** sheets can be rapidly thermoformed at low energy consumption without predrying, while retaining their frosted surface. The result: shorter production cycles, extreme degrees of stretching and accurate mould surface reproduction. In addition, the sheets are easy to screen print and machine.

	Test Conditions	Typical Values	Unit	Test Method
<b>PHYSICAL</b>				
Density		1.27	g/cm <sup>3</sup>	ISO 1183-1
Moisture absorption	after storage in standard climate 23 °C/ 50 % RH	0.2	%	ISO 62-4
	after storage in water at 23 °C until saturation	0.6	%	ISO 62-1
Gloss	20°	<7		DIN EN ISO 2813
<b>MECHANICAL</b>				
Tensile stress	at yield	> 45	MPa	ISO 527-2/1B/50
Elongation	at yield	4	%	ISO 527-2/1B/50
Tensile strength		> 45	MPa	ISO 527-2/1B/50
Elongation	at break	> 35	%	ISO 527-2/1B/50
Elastic modulus		2020	MPa	ISO 527-2/1B/1
Limiting flexural stress		ca. 80	MPa	ISO 178
Impact strength	Charpy, unnotched	no break	kJ/m <sup>2</sup>	ISO 179/1fU
	Charpy, notched	ca. 7	kJ/m <sup>2</sup>	ISO 179/1eA
	Izod, notched	ca. 6	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL</b>				
Vicat softening temperature	Method B50	80	°C	ISO 306
Thermal conductivity		0.2	W/m K	DIN 52612
Coeff. of linear thermal expansion		0.05	mm/m K	DIN 53752-A
Heat deflection temperature under load	Method A: 1.80 MPa	63	°C	ISO 75-2
	Method B: 0.45 MPa	70	°C	ISO 75-2
<b>ELECTRICAL</b>				
Dielectric strength		16.1	kV/mm	IEC 60243-1
Volume resistivity		10 <sup>15</sup>	Ohm-cm	IEC 60093
Surface resistivity		10 <sup>16</sup>	Ohm	IEC 60093
Dielectric constant	at 10 <sup>3</sup> Hz	2.6		IEC 60250
	at 10 <sup>6</sup> Hz	2.4		IEC 60250
Dissipation factor	at 10 <sup>3</sup> Hz	0.005		IEC 60250
	at 10 <sup>6</sup> Hz	0.02		IEC 60250

The mechanical properties were measured on sheets of 4 mm thickness.

Product Liability Clause: This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided – especially that contained in our safety data and technical information sheets – and to test products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.



**VIVAK®**  
DESIGN



Product data sheet, June 2010

# Vivak® Design

## Frosted solid copolyester sheets



**i-line**

Ideas, innovative, intelligent, interesting, ...

Bayer Sheet Europe i-line represents the next generation of quality products. This seal guarantees innovative and intelligent first-class solutions at all times for a multitude of requirements.

**Light Transmission:**

Test Method according to DIN 5036

The stated thicknesses are all available as standard. Please ask us for more information.

The stated values are typical values only.

Light transmission in %	2	3	4	5
Vivak® Design clear 099	75 %	75 %	74 %	74 %
Vivak® Design white 145	53 %	43 %	34 %	28 %

**Available sizes:**

**Vivak® Design** is available in thicknesses from 2 to 5 mm and in the following colours and formats.

**Colors:**

Vivak® Design clear 099

Vivak® Design white 145

**Size (Standard):**

2,050 x 1,250 mm

Other sizes, colours and sheet thicknesses available on request.

**Thermoforming:**

Owing to their outstanding flow and mould surface reproduction, **Vivak® Design** sheets can be thermoformed at low temperatures without predrying. Because of its low specific heat capacity, Vivak® requires only a little amount of energy for thermoforming.

**Permanent Service Temperature:**

The permanent service temperature without load is approx. 65 °C.

**Fire rating(\*):** Oxygen index (LOI) 26 % ISO 4589

Country	Standard	Rating	Thickness	Color
Europe	EN13501-1	B-s1, d0	2 - 5 mm	clear 099
UK	BS 476 Part 7	Class 1Y	2 + 5 mm	clear 099
Germany	DIN 4102	B1 (Indoor)	2 - 5 mm	clear 099 + all colors
Belgium	BS 476	A1	2 + 5 mm	clear 099

(\* fire certificates are limited in time, always check if the mentioned certificate is still valid.

Bayer Sheet Europe also produces multiwall sheets in polycarbonate (Makrolon® multi UV), and solid sheets in polycarbonate (Makrolon® GP) and in polyester (Vivak® and Axpert®). For more information, take a look at [www.bayersheeteurope.com](http://www.bayersheeteurope.com)

Bayer Sheet Europe GmbH  
 Otto-Hesse-Straße 19/T9, 64293 Darmstadt, Germany  
 Tel. +49 6151 13 03-0  
 Fax +49 6151 13 03-500  
[www.bayersheeteurope.com](http://www.bayersheeteurope.com)  
[sales@bayersheeteurope.com](mailto:sales@bayersheeteurope.com)

A  Bayer MaterialScience Company



**VIVAK®**  
DESIGN